



14700 Downey Avenue  
P.O. Box 1418  
Paramount, CA 90723-1418  
(562) 531-2060

**PRODUCT SPECIFICATIONS**

**PRODUCT:** ASPHALT CEMENT

**GRADE:** AC-40 (Arizona) **PRODUCT CODE:** 13421

**DESCRIPTION:** A vacuum steam refined straight run asphalt for use in hot mixes in warmer temperature climates under normal load conditions.

**MEETS SPECIFICATIONS:** ASTM D3381, Table 1  
AASHTO M226, Table 1

TESTS	ASTM METHOD	AASHTO METHOD	SPECS.	TYPICAL ANALYSIS <sup>1</sup>
Original Asphalt:				
Abs. Viscosity, 140°F, Poise	D2171	T202	3200-4800	3560
Kin. Viscosity, 275°F, cSt	D2170	T201	300 min	361
Penetration, 77°F, 100g, 5s	D5	T49	20 min	31
Flash Point, P.M.C.C °F	D93	T73	450 min	465
Solubility in TCE, wt. %	D2042	T44	99.0 min	99.9
Specific Gravity, 77/77 °F	D70	T228		1.019
Specific Gravity, 60/60 °F	D70	T228		1.025
API Gravity, 60°F	D70	T228		6.6
Density, 60°F, Lbs/Gallon	D70	T228		8.53
Residue from R.T.F.O. Test:				
Abs. Viscosity, 140°F, Poise	D2171	T202	16000 max	8480
Aging Index, 140°F	D2171	T202		2.4
Kin. Viscosity, 275°F, cSt	D2170	T201		535
Penetration, 77°F, 100g, 5s	D5	T49		21
% of Original Penetration	D5	T49		68
Penetration, 4°C, 200g, 60s	D5	T49		8
Ductility, 77°F, 5cm/min, cm	D113	T51	75 min	100+
Loss on Heating, wt. %	D2872	T240		0.2

<sup>1</sup>Values shown as typicals may, at times, be superseded by results which are current at a particular time.

**AVAILABILITY:** Readily available Phoenix Terminal

**DOT SHIPPING NAME:** UN3257, Elevated temperature liquid, n.o.s., 9, III

**DOT PLACARD:** Hot, 3257

**RELEASED:** 02-01-2003